

⑩ 日本国特許庁 (JP)

⑪ 特許出願公開

⑫ 公開特許公報 (A)

昭59-98726

⑬ Int. Cl.³
B 01 J 12/00
C 01 B 13/20

識別記号

庁内整理番号
6542-4G
7918-4G

⑭ 公開 昭和59年(1984)6月7日

発明の数 1
審査請求 未請求

(全 2 頁)

⑮ 酸化膜形成法

⑯ 特 願 昭57-207406

⑰ 出 願 昭57(1982)11月26日

⑱ 発 明 者 岩松誠一

諏訪市大和3丁目3番5号株式

会社諏訪精工舎内

⑲ 出 願 人 株式会社諏訪精工舎

東京都中央区銀座4丁目3番4号

⑳ 代 理 人 弁理士 最上務

明 細 書

発明の名称

酸化膜形成法


特許請求の範囲

SiO₂ 膜、Al₂O₃ 膜等の酸化膜を化学蒸着法で形成する方法に関し、シラン・ガス (SiH₄、SiH₂Cl₂)、アルミニウム・エチレート Al(OC₂H₅)₃ 等のガス体と水蒸気または過酸化水素蒸気を含む密封気内に試料基板を加熱して設置し、酸化膜を形成することを特徴とする酸化膜形成法。

発明の詳細な説明

本発明は低温化学蒸着酸化膜形成法に関する。

従来、酸化膜の形成法としては、化学蒸着法の場合、例えば SiO₂ 膜形成の場合の代表例として、



の反応により SiO₂ 膜を形成するのが通例であった。

しかし、上記従来技術では、化学蒸着温度が 350℃ 程度以下にできないという欠点があった。

本発明はかかる従来技術の欠点をなくし、低温で酸化膜を化学蒸着法で提供することを目的とする。

上記目的を達成するための本発明の基本的な構成は酸化膜を化学蒸着法で形成する方法に関し、化合物ガスと水蒸気または過酸化水素蒸気を含む密封気内に試料基板を加熱して設置することを特徴とする。


以下、実施例により本発明を詳述する。

第1図は本発明による酸化膜形成法の一例を模式的に示したものである。石英反応管1内には SiH₄ ガス配管2、H₂O、バブラー5を60℃ 程度に加熱するヒーター4により加熱した H₂O、含有水をバブルする窒素ガスを配管5より供給して、配管6より H₂O₂ 蒸気を供給する。石英反

特開昭59- 98726(2)

応管 1 内には試料 7 が設置され、該試料 2 はヒーター 8 により 200℃ 程度に加熱される。排ガスは配管 9 より排出される。

上記の如き方法により、



の反応により 200℃ 程度の低温で SiO_2 膜が形成できる。

本発明は SiO_2 膜に限らず、 Al_2O_3 等他の化学蒸着膜形成にも用いることができる。

本発明は少なくとも過酸化水素蒸気を必要とし、その他酸素、水蒸気、オゾン、窒素等のガスを同時に含んでも良い。

図面の簡単な説明

第 1 図は本発明による酸化膜形成法の一例を示す化学蒸着法の模式図である。

1 …… 反応管

2, 3, 5, 9 …… 配管


4, 8 …… ヒーター

7 …… 試料基板

以 上

出願人 株式会社敬勤精工舎

代理人 舟越士 敏上



第 1 図

Japanese Kokai Patent Application No. Sho 59[1984]-98726

Translated from Japanese by the Ralph McElroy Co., Custom Division
P.O. Box 4828, Austin, Texas 78765 USA

Code: 2037-60269

Ref. No.: APPM/0001/PDD/MBE

JAPANESE PATENT OFFICE

PATENT JOURNAL

KOKAI PATENT APPLICATION NO. SHO 59[1984]-98726

Int. Cl. ³ :	B 01 J 12/00 C 01 B 13/20
Sequence Nos. for Office Use:	6542-4G 7918-4G
Application No.:	Sho 57[1982]-207406
Application Date:	November 26, 1982
Publication Date:	June 7, 1984
No. of Inventions:	1 (Total of 2 pages)
Examination Request:	Not requested

OXIDE FILM-FORMING METHOD

Inventor:	Seiichi Iwamatsu Suwa Seikosha Co., Ltd. 3-3-5 Owa, Suwa-shi
Applicant:	Suwa Seikosha Co., Ltd. 4-3-4 Ginza, Chuo-ku, Tokyo
Agent:	Tsutomu Mogami, patent attorney

[There are no amendments to this patent.]


Claim

An oxide film-forming method, characterized by the fact that, in regard to a method for the formation of a SiO_2 film, an Al_2O_3 film and other oxide films by the chemical vapor deposition method, a sample substrate is heated and installed to form an oxide film in an atmosphere containing a silane gas (SiH_4 , SiHCl_3), aluminum ethylate ($\text{Al}(\text{OC}_2\text{H}_5)_3$) and other gases and steam or hydrogen peroxide vapors.

Detailed explanation of the invention

The present invention relates to a low-temperature chemical vapor deposition oxide film-forming method.

Conventionally, as a method for the formation of an oxide film, in the case of the chemical vapor deposition method, for example, as a typical example for the formation of a SiO_2 film, it is common to form a SiO_2 film by the reaction of



However, in the above-mentioned prior art, there has been a disadvantage in which the chemical vapor deposition temperature cannot be less than 350°C or so.


The present invention has an objective to provide a low-temperature oxide film by the chemical vapor deposition method, with the elimination of the disadvantage of the prior art.

The basic constitution of the present invention for achieving the above-mentioned objective relates to the method for the formation of an oxide film by the chemical vapor deposition method. It is characterized by the fact that a sample substrate is heated and installed in an atmosphere containing a compound gas and steam or hydrogen peroxide vapors.

The present invention will be explained in detail with the following application example.

Figure 1 schematically shows an example of the oxide film-forming method according to the present invention. In the quartz reaction tube (1), SiH_4 is supplied from the SiH_4 gas pipe (2). Nitrogen gas is supplied from a pipe (5) for bubbling H_2O_2 -containing water heated by a heater (4) for heating the H_2O_2 bubbler (3) to 60°C or so. The H_2O_2 vapors are supplied from the pipe (6). In the quartz reaction tube (1), a sample (7) is installed. Said sample (2) [sic; 7] is heated to 200°C or so by the heater (8). The effluent gas is discharged from the pipe (9).

By the method described above, a SiO_2 film can be formed at a low temperature of 200°C or so by the reaction,



The present invention is not restricted to SiO_2 film. It can also be used in the formation of an Al_2O_3 film and other chemical vapor deposition films.

In the present invention, at least hydrogen peroxide vapors are required. In addition, oxygen, steam, ozone, nitrogen, and other gases may also be contained simultaneously.

Brief description of the figure

Figure 1 is a schematic diagram of the chemical vapor deposition method showing an example of the oxide film-forming method according to the present invention.

- 1 Reaction tube
 2,3,5, 9 Pipes
 4,5 Heaters.




Figure 1

⑨ 日本国特許庁 (JP)

⑩ 特許出願公開

⑫ 公開特許公報 (A)

昭59-98726

⑪ Int. Cl.³
B 01 J 12/00
C 01 B 13/20

識別記号

庁内整理番号
6542-4G
7918-4G

⑬ 公開 昭和59年(1984)6月7日

発明の数 1
審査請求 未請求

(全 2 頁)

⑭ 酸化膜形成法

⑮ 特 願 昭57-207406

⑯ 出 願 昭57(1982)11月26日

⑰ 発 明 者 岩松誠一

諏訪市大和3丁目3番5号株式

会社諏訪精工舎内

⑱ 出 願 人 株式会社諏訪精工舎

東京都中央区銀座4丁目3番4号

⑲ 代 理 人 弁理士 最上務

明 細 書

発明の名称

酸化膜形成法


特許請求の範囲

S i O₂ 膜、A l₂O₃ 膜等の酸化膜を化学蒸着法で形成する方法に関し、シラン・ガス (S i H₄、S i H C l₃)、アルミニウム・エチレート A l (O C₂H₅)₃ 等のガス体と水蒸気または過酸化水素蒸気を含む気相内に試料基板を加熱して設け、酸化膜を形成することを特徴とする酸化膜形成法。

発明の詳細な説明

本発明は低温化学蒸着酸化膜形成法に関する。

従来、酸化膜の形成法としては、化学蒸着法の例、例えば S i O₂ 膜形成の場合の代表例として、



の反応により S i O₂ 膜を形成するのが通例であった。

しかし、上記従来技術では、化学蒸着温度が 350℃ 程度以下にできないという欠点があった。

本発明はかかる従来技術の欠点をなくし、低温、酸化膜を化学蒸着法で提供することを目的とする。


上記目的を達成するための本発明の基本的な構成は酸化膜を化学蒸着法で形成する方法に関し、化合物ガスと水蒸気または過酸化水素蒸気を含む気相内に試料基板を加熱して設け、酸化膜を形成することを特徴とする。

以下、実施例により本発明を詳述する。

第1図は本発明による酸化膜形成法の一例を模式的に示したものである。石英反応管1内には S i H₄ ガス配管2、H₂O、バブラー3を60℃ 程度に加熱するヒーター4により加熱した H₂O、含有水をバブルする窒素ガスを配管5より供給し、配管6より H₂O、蒸気を供給する。石英反

反応管1内には試料7が設置され、該試料2はヒーター8により200℃程度に加熱される。排ガスは配管9より排出される。

上記の如き方法により、



の反応により200℃程度の低温で SiO_2 膜が形成できる。

本発明は SiO_2 膜に限らず、 Al_2O_3 等の化学蒸着膜形成にも用いることができる。

本発明は少なくとも過酸化水素蒸気を必要とし、その他酸素、水蒸気、オゾン、窒素等のガスを同時に含んでも良い。


図面の簡単な説明

第1図は本発明による酸化膜形成法の一例を示す化学蒸着法の模式図である。

1……反応管

2, 3, 5, 9……配管

4, 8……ヒーター



第1図

出願人 株式会社東紡精工会

代理人 弁護士 最上

